



Patent Knotting **Technical Data Sheet**

Description

Bartoline Patent Knotting is a quick drying solution for sealing knots and resinous areas of bare timber, prior to the application of paints, waxes or polishes.

Preparation

Ensure that the wood to be treated is thoroughly clean and dry. Remove excess resinous matter or loose particles. Shake container well before use.

Application

Apply 1-2 liberal coats using a brush, or lint free cloth. Allow to dry between coats. Touch dry in 5-10 minutes. Can be re-coated after 30 minutes under normal conditions. When the treated area is to be over-coated with a water-based coating system, apply the knotting solution more sparingly, and once dry lightly abrade the surface to provide a key before over-coating.

After Care

Replace lid firmly after use. Store away from heat and flames. Clean all tools and application equipment with Bartoline Methylated Spirit and rinse thoroughly.

Health and Safety

See MSDS for full information.

Technical Data

Measurement	Value	Test Method
Physical State	Liquid	Visual
Colour	Brown	Visual
Odour	Alcoholic	
Initial Boiling Point	75 - 78°C	
Flash Point	12°C	
Density	0.80 – 0.93	

Packing Specification

<u>Pack Size</u>	<u>Product Code</u>	<u>Pack Barcode</u>	<u>Carton Barcode</u>	<u>Packs Per Carton</u>	<u>Cartons Per Pallet</u>	<u>Packs Per Pallet</u>	<u>Ti</u>	<u>Hi</u>
500ml	55625000	5010789625009	05010789259280	6	156	936	39	4

Customs Tariff Code

3210 0010

Shipping Classification

Correct Shipping Name: Paint (Ethanol)

Classification: Class 3

UN Number: UN 1263

Packing Group: II

Additional Information: Marine Pollutant